

CRACKMASTER SUPREME
Hot Pour Crack Sealant

SMT-190

REVISED 03/20/23

PRODUCT DESCRIPTION

CrackMaster Supreme is a single component, hot applied crack and joint sealant. CrackMaster Supreme is specially formulated for both direct fire and oil-jacketed melters. It is heat stabilized to withstand temperatures up to 450°F without experiencing polymer degradation. When melted and properly applied it forms a resilient crack sealant for both asphaltic and cementitious pavements. CrackMaster Supreme meets manufacturer's specifications.

USES

CrackMaster Supreme is designed to seal expansion joints, longitudinal and transverse cracks, joints between concrete and asphalt shoulders, and random cracks in both asphalt and concrete pavements. CrackMaster Supreme is relatively hard and has a high softening point, which makes it well suited for parking lots and driveways.

COMPOSITION

As supplied, CrackMaster Supreme is supplied in solid blocks comprised of heat stabilized polymers and asphalt.

COLOR

Black.

LIMITATIONS

Do not overheat material. Cracks must be free from moisture, dust, loose aggregate and other contaminants prior to application. Not recommended for cracks in excess of 1" wide.

TECHNICAL DATA

CrackMaster Supreme meets SealMaster Product Specification when tested in accordance with ASTM D5329. (see chart below).

Chemical & Physical Analysis	
Recommended Pour Temperature	350-400°F
Maximum Heating Temperature	450°F
Cone Penetration at 25°C	50 max.
Flow at 60°C, mm	0
Softening Point	200°F Min
Flexibility 0°F	(1" Mandrel) - PASS
Specific Gravity	1.17
Asphalt Compatibility	PASSES

ENVIRONMENTAL CONSIDERATIONS

CrackMaster Supreme is considered a non-hazardous material.

INSTALLATION

Proper surface preparation will facilitate adequate adhesion and consequently the maximum service life of the sealant. The crack must be free from moisture, dust, and loose aggregate. Routing or wire brushing are preferred methods followed by a compressed air heat lance immediately prior to sealing. The substrate and air temperature must be above 40°F.

METHODS

CrackMaster Supreme shall be melted in direct fired or oil jacketed melters. Carefully insert blocks of material (with plastic bag) into the melting equipment while the agitator is turned off. Load material slowly to avoid splashing. After the initial load of material has reached the recommended pouring temperature (350-400°F), fresh material may be added as sealant is used. Melt only enough material that will be used the same day. Avoid overheating material. Excessive heat could cause material to gel in the equipment or fail in crack and joints. A significant viscosity increase accompanied by stringiness signals the approach of gelation. If this occurs, immediately remove the material from the melter and dispose of it.

IMPORTANT

Protective apparel is recommended with application of CrackMaster Supreme. The extremely hot material will cause severe burns on contact with skin. OSHA Safety Regulations require workers to wear the following types of safety attire (see current OSHA/Safety Regulations for additional information): Hard hat with face shield; long sleeved shirt buttoned at the wrist; heat resistant gloves; long, cuffless pants; and safety toed work boots. Make certain all area around melter is clear of all debris and flammable materials. Avoid breathing vapors. Use with adequate ventilation.

MIXING PROCEDURES

Use material as supplied. Do not blend with other materials.

APPLICATION

Apply heated CrackMaster Supreme using either a pump and wand system or a pour pot. For best results the sealant depth to width ratio should not exceed 2 to 1 (i.e. 2-inches deep to 1-inch wide). The cooled sealant height should not exceed 1/8" above surrounding pavement. Using a sealing shoe or squeegee, band the material 2 to 3 inches wide over the crack.

CRACKMASTER SUPREME

Hot Pour Crack Sealant

SMT-190

REVISED 03/20/23

ESTIMATING MATERIAL REQUIREMENTS

Use the following chart as a guideline for estimating material requirements (based upon pounds of material needed for 100 feet of cracks):

Crack Width	Depth	Lbs/100 Ft
3/8"	3/8"	6.2 lbs.
3/8"	1/2"	8.3 lbs.
1/2"	1/2"	11.1 lbs.
1/2"	1"	22.2 lbs.
3/4"	1/2"	16.6 lbs.
3/4"	3/4"	25.00 lbs.

The above coverage rates are only a guideline. Actual material usage may vary due to width of application and thickness of material above pavement surfaces.

PRECAUTIONS

Cracks must be free from moisture, dust, dirt, and debris. Both substrate and air temperature must be above 40°F. Keep boxes of material dry during storage. Do not store in direct sunlight.

PACKAGING AND AVAILABILITY

CrackMaster Supreme is supplied in both meltable packaging and cardboard cartons. CrackMaster Hot Pour Crack Sealants are supported by a nationwide network of SealMaster facilities along with a national and international network of professional applicators.

WARRANTY AND DISCLAIMER

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workmanship, weather, construction, condition of pavement, tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose.



Phone: 1-800-395-7325

www.sealmaster.net