

# LIQUID ROAD ULTRA

*For Application on Roads*  
*Factory Blended with Aggregate*

**SMT-156**

REVISED 04/06/23

## PRODUCT DESCRIPTION

LIQUID ROAD ULTRA PAVEMENT SEALER FOR ROADS is a polymer-modified, fiber reinforced asphalt emulsion coating that contains specifically graded aggregate and is applied to bituminous pavement surfaces. Liquid Road Ultra is a ready to apply material that is factory blended with aggregate. Liquid Road Ultra is a highly durable, slip-resistant surface treatment that greatly extends pavement service life. Liquid Road Ultra Pavement Sealer meets ASTM D8099/D8099M-17 Standard Specification for Asphalt Emulsion Pavement Sealer.

## USES

Liquid Road Ultra is ideal for protecting and beautifying all types of pavement surfaces including Roads, Streets, Parking Lots, Shopping Malls, Driveways, Roadways and more. This particular specification pertains to Liquid Road Ultra application on Roads and Streets. (For application on parking lots, see SMT-155)

## ESTIMATING MATERIAL REQUIREMENTS

One gallon of Liquid Road Ultra for application on Roads and Streets will cover approximately 33-37 square feet per coat (3.66-4.11 square yards per coat). Multi-coat application is recommended for optimum durability (See APPLICATION PROCEDURES below).

## APPLICATION RATE

Apply Liquid Road Ultra for applications on Roads and Streets at a rate of 33-37 square feet per coat (3.66-4.11 square yards per coat). Application rates may vary due to pavement porosity and method of application.

## PERFORMANCE CHARACTERISTICS

Table 1 - Physical Requirements Of Liquid Road Ultra For Road Application		
ASTM	Test Description	Result
D2939-8	Residue by Evaporation, %	45-65%
E303	Measuring Surface Frictional Properties- British Pendulum Tester	Min. 60 BPN
E274	Locked Wheel Skid Testing	> 30 SN
D4060	Abrasion Resistance- Taber Abraser Dry Method	< 1% Loss
D3910-6.4	Wet Track Abrasion Test	< 25g/ft <sup>2</sup> Loss
D5	Penetration of Bituminous Materials-Base Asphalt	12-45 Pen
D113	Ductility of Bituminous Materials-Base Asphalt	5-15 cm
Std. %	Percent Polymer Solids to Asphalt by wt.	3% min.
E70	PH of Aqueous Solutions with Glass Electrodes	6-10 PH
D6378	Vapor Pressure (VPX), mm Hg @ 25° C (77° F)	22-26 mm Hg
D36	Softening Point of Emulsion Residue (Ring and Ball Apparatus)	> 200° F
D562	Viscosity using a Stormer-Type Viscometer	60-110 KU

D870	Water Resistance of Coatings using Water Immersion	No Delamination
D6904	Resistance to Wind-Driven Rain	No Delamination
D4585	Water Resistance of Coatings Using Controlled Condensation	No Delamination
D1735	Water Resistance of Coatings Using Water Fog Apparatus	No Delamination
D2247	Water Resistance of Coatings in 100% Relative Humidity	No Delamination
D4541	Adhesion Strength over Asphalt Pavement	> 200 PSI
D2939-7	Weight per Gallon	10-12 lbs./gal
D2939-13	Drying Time- 50% humidity, 73.4 ± 3.6°F	2-6 Hrs.
D2939-14	Resistance to Heat- No Blistering, sagging or slipping	PASS
D2939-15	Resistance to water- No softening, delamination or re-emulsification	PASS
D2939-16	Flexibility- No Cracking or Delamination	PASS
D2939-26	Resistance to Impact- No Chipping, Cracking or Delamination	PASS
D2939-27	Resistance to Impact After Accelerated Weathering	PASS
D4799	QUV UV Aging-1,000 Hours	No Color Fade
D3359	Measuring Adhesion by Tape- No More than a Trace of Peeling	PASS
Volatile Organic Compounds	Determination of Volatile Organic Compounds (VOC) in various Coatings	< 10 g/l
PAH Content (Percentage)	Polycyclic Aromatic Hydrocarbon Content (Percentage)	Less than one-tenth of 1% (< .10%)
D2939-5	Uniformity	PASS
D2939-22	Wet Film Continuity	PASS
D95	Water Content, %	35-55%
D2939-10	Ash Content of Residue, %	60-68%

## SURFACE PREPARATIONS

Surface must be clean and free from loose material and dirt. Cracks should be filled with SealMaster Cold or Hot-Applied Crack Filling Materials. Oil stains should be cleaned and primed with SealMaster Oil Spot Primer.

## APPLICATION EQUIPMENT

Liquid Road Ultra for Roads shall be applied by mechanical squeegee and or brush equipment. Equipment shall have continuous agitation or mixing capabilities to maintain homogeneous consistency of mixed material throughout the application process. Truck mount or self-propelled squeegee/brush equipment shall have at least 2 squeegee or brush devices (one behind the other) to assure adequate distribution and penetration of Liquid Road Ultra into bituminous pavement. Hand squeegees and brushes shall be acceptable in areas where practicality prohibits the use of mechanized equipment.

# LIQUID ROAD ULTRA

## *For Application on Roads*

### *Factory Blended with Aggregate*

**SMT-156**

REVISED 04/06/23

**MIXING PROCEDURES**

Mix Liquid Road Ultra thoroughly before applying. If needed, a small amount of water may be added to facilitate application.

**APPLICATION PROCEDURES**

To achieve optimum performance and the desired results for Liquid Road Ultra, it is important to follow proper application procedures. The following two coat process is recommended for optimum performance and durability:

1. Apply, by squeegee application, the first coat of Liquid Road Ultra at a rate of 33-37 square feet (3.66-4.11 square yards) per gallon. Allow first coat to dry thoroughly before applying the second coat.
2. Apply, by squeegee application, the second coat of Liquid Road Ultra at a rate of 33-37 square feet (3.66-4.11 square yards) per gallon. Allow second coat to dry thoroughly before opening to traffic.

**APPLICATION WEATHER CONDITIONS**

Liquid Road Ultra shall not be applied when temperature is expected to drop below 50° F during application and for a period of at least 24 hours after application. Do not apply if rain is imminent or forecast within 12 hours.

**LINE STRIPING AND TRAFFIC MARKINGS**

Use SealMaster Traffic Paints for line striping and traffic markings.

**PACKAGING AND AVAILABILITY**

Liquid Road Ultra is available for plant pick up or bulk tanker load quantities. Liquid Road Ultra is supported by a national network of SealMaster manufacturing and distribution facilities along with a national network of qualified applicators.

**WARRANTY AND DISCLAIMER**

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workmanship, weather, construction, condition of pavement, tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose.

Copyright © InFrasys, Inc. All rights reserved. Reproduction of any of this material is strictly prohibited.



Phone: 1-800-395-7325

[www.sealmaster.net](http://www.sealmaster.net)